



US 6,294,487 B1

2162

(12) **United States Patent**  
**Keshavaraj**

(10) **Patent No.:** **US 6,294,487 B1**  
 (45) **Date of Patent:** **Sep. 25, 2001**

(54) **AIRBAG FABRIC PROCESSING VERY LOW COVER FACTOR**

(75) **Inventor:** **Ramesh Keshavaraj, LaGrange, GA (US)**

(73) **Assignee:** **Milliken & Company, Spartanburg, SC (US)**

(\*) **Notice:** Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) **Appl. No.:** **09/405,999**

(22) **Filed:** **Sep. 24, 1999**

(51) **Int. Cl.<sup>7</sup>** ..... **B32B 5/08**

(52) **U.S. Cl.** ..... **442/218; 280/728.1; 428/34.3; 428/34.5; 428/34.6; 428/34.7; 428/36.1; 442/76; 442/152; 442/158; 442/164; 442/168; 442/181; 442/203**

(58) **Field of Search** ..... **280/728.1; 428/34.3; 428/34.5, 34.6, 34.7, 36.1; 442/76, 152, 158, 164, 168, 181, 203, 218**

(56) **References Cited**

#### U.S. PATENT DOCUMENTS

3,792,873	2/1974	Buchner et al.	280/150 AB
4,921,735	5/1990	Bloch	428/34.9
4,944,529	7/1990	Backhaus	280/743
5,087,071	2/1992	Wallner et al.	280/743
5,090,729	2/1992	Watanabe	280/743
5,093,163	3/1992	Krummheuer et al.	428/35.1
5,110,666	5/1992	Menzel et al.	428/196
5,215,795 *	6/1993	Matsumoto et al.	428/36.1
5,236,775	8/1993	Swoboda et al.	428/225
5,277,230	1/1994	Sollars, Jr.	139/389
5,310,216	5/1994	Wehner et al.	280/743 R
5,316,337	5/1994	Yamaji et al.	280/743 R
5,356,680	10/1994	Krummheuer et al.	428/36.1
5,365,651	11/1994	Rogers et al.	29/468
5,405,164	4/1995	Paxton et al.	280/728 A
5,407,223	4/1995	Lauritzen et al.	280/728 A
5,423,273	6/1995	Hawthorn et al.	112/441
5,454,587	10/1995	Halford et al.	280/728.1
5,454,594	10/1995	Krickl	280/743.1

5,458,364	10/1995	Mueller et al.	280/728.2
5,477,890	12/1995	Krummheuer et al.	139/291 R
5,498,024	3/1996	Caruso, Jr.	280/728.2
5,503,197	4/1996	Bower et al.	139/435.1
5,508,073	4/1996	Krummheuer et al.	428/35.1
5,520,414	5/1996	Bishop	280/743.1
5,533,755	7/1996	Nelsen et al.	280/743.1
5,544,911	8/1996	Vine	280/728.2
5,547,212	8/1996	Dyer et al.	280/728.2
5,553,886	9/1996	Gunn et al.	280/728.2
5,564,738	10/1996	Johnson	280/736
5,564,739	10/1996	Davidson	280/736
5,566,973	10/1996	Green et al.	280/728.2
5,620,200	4/1997	Garner et al.	280/728.2
5,652,389	7/1997	Schaps et al.	73/643
5,683,100	11/1997	Enders	280/728.2
5,692,777	12/1997	Tochacek et al.	280/743.1
5,704,402	1/1998	Bowen et al.	139/289
5,709,405	1/1998	Saderholm et al.	280/736
5,952,250 *	9/1999	Kim et al.	442/203
6,220,309 *	4/2001	Sollars, Jr.	139/389

\* cited by examiner

*Primary Examiner*—Elizabeth M. Cole

*Assistant Examiner*—Arti R. Singh

(74) *Attorney, Agent, or Firm*—Terry T. Moyer; William S. Parks

(57) **ABSTRACT**

The present invention relates to an airbag fabric which is woven in such a manner as to possess a cover factor of less than about 1900 but which simultaneously, through the presence of a film (laminate) or coating, possesses an extremely low air permeability. The utilization of such a loosely constructed fabric within airbag cushions has heretofore not been possible, even with the application of standard airbag coatings (such as silicones) over the fabric surface since such coatings with not easily remain in contact over the loosely constructed fabric surface (i.e., the coating would leak through the fabric). The coupling of a low cover factor fabric with a laminate film (or with a coating wherein the cover factor is at least 1600), however, solves such a problem and permits the utilization of inexpensively produced woven fabrics within airbag applications.

**20 Claims, No Drawings**

30066733 020402